



System Three Resins, Inc.
 3500 W. VALLEY HWY. N. SUITE 105
 AUBURN, WASHINGTON 98001
 TECHNICAL SUPPORT: 253-333-8118

TECHNICAL DATA SHEET

**QuikFair™
 EPOXY
 FAIRING PUTTY**

DESCRIPTION:

QuikFair™ is a light-weight, microballoon-filled, epoxy fairing putty with excellent moisture resistance. It is designed to be used on both fiberglass and wood-epoxy boats above or below the waterline. The two color-coded parts have non-sagging, buttery consistency and are easily and quickly mixed. At 70°F, Quikfair mixed with the Fast Hardener (Part B) will be sufficiently cured to hand or block-sand in 3 hours or power-sanded in 4 hours. This allows the user to apply three coats each 24 hours in a standard eight-hour shift or six in a round-the-clock basis. QuikFair with Fast Hardener allows the user to complete a fairing or filleting job in a day rather than three or four days.

PHYSICAL PROPERTIES:

Viscosity @ 25°C(77° F) cps
 Density (lb. per gallon)
 Color

	Part A	Part B Fast	Part B Slow
Viscosity @ 25°C(77° F) cps	480,000	480,000	480,000
Density (lb. per gallon)	6.8	6.4	6.4
Color	Tan	White	Blue
MIXED SYSTEM PROPERTIES:			
Viscosity @ 25°C(77° F) cps	480,000	480,000	480,000
Mix ratio by volume resin/hardener	100	50	50
Mix ratio by weight resin/hardener	100	44	44
Working time(100g @ 25°C)	N/A	10 min.	60 min.
Time to sand* (block or hand)	N/A	3 hours	8 hours
(DA or random-orbit)		4 hours	10 hours

MIXED SYSTEM PROPERTIES:

Viscosity @ 25°C(77° F) cps
 Mix ratio by volume resin/hardener
 Mix ratio by weight resin/hardener
 Working time(100g @ 25°C)
 Time to sand* (block or hand)
 (DA or random-orbit)

APPLICATION:

Ensure surfaces to be faired are clean, free, of dust, grease, or dirt. Sand surface with 80-120 grit paper. Measure and mix only enough Quikfair that can be applied in the indicated working time.

- QuikFair’s buttery consistency makes it easy to measure by weight or volume
- To ensure good adhesion, always sand QuikFair and before applying additional coats of putty, resin or any coating or finish.
- For best results, apply at 50° F or above.

Kit sizes available(kits): 1½-pint / 1½-quart / 3-quart / 1½-gallon

For health and safety information concerning this product, please refer to the MSDS sheets for Silvertip QuikFair Epoxy Fairing Putty. MSDS sheets are available on our website at www.systemthree.com, or by calling or writing System Three Technical Support.

The information contained herein is based on the data available to us and is believed to be correct. However, System Three Resins, Inc. makes no warranty, expressed or implied, regarding the accuracy of these data or the results to be obtained from the use thereof. System Three assumes no responsibility for injury from the use of the product described herein.